


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B01D 71/02 // C25D 11/02	A1	(11) International Publication Number: WO 91/04785 (43) International Publication Date: 18 April 1991 (18.04.91)
(21) International Application Number: PCT/CA90/00329 (22) International Filing Date: 28 September 1990 (28.09.90) (30) Priority data: 8922069.3 29 September 1989 (29.09.89) GB (60) Parent Application or Grant (63) Related by Continuation US 497,554 (CIP) Filed on 22 March 1990 (22.03.90) (71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street, West, Montreal, Quebec H3A 3G2 (CA). (72) Inventors; and (75) Inventors/Applicants (for US only) : ROSENFELD, Aron, Marcus [CA/CA]; 64 Ontario Street, #708, Kingston, Ontario K7L 5J4 (CA). JOZEFOWICZ, Mark, Adrian [CA/CA]; 294 College Street, Kingston, Ontario K7L 4M4 (CA). FURNEAUX, Robin, Christopher [GB/GB]; Lady Barn, The Level, Sherington, Banbury, Oxon OX15 6NA (GB). THOMAS, Michael, Patrick [GB/CA]; The Berriefield, R.R. #2, Kingston, Ontario K7L 5H6 (CA).		(74) Agents: GALE, Edwin, J. et al.; Kirby, Eades, Gale, Baker & Potvin, Box 3432, Station D, Ottawa K1P 6N9 (CA). (81) Designated States: AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH (European patent), CM (OAPI patent), DE (European patent)*, DK (European patent), ES (European patent), FI, FR (European patent), GA (OAPI patent), GB (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI patent), MR (OAPI patent), MW, NL (European patent), NO, RO, SD, SE (European patent), SN (OAPI patent), SU, TD (OAPI patent), TG (OAPI patent), US. Published <i>With international search report.</i> <i>With amended claims and statement.</i>

(54) Title: POROUS MEMBRANES SUITABLE FOR SEPARATION DEVICES AND OTHER USES

**(57) Abstract**

Porous membranes incorporating porous anodic films are disclosed. The membranes, which may be used as filters, gaseous diffusion media, dialysis membranes, etc., are produced by porous anodizing aluminum or other porous anodizable metal, creating a weakened stratum in the resulting porous anodic film (e.g. by a voltage reduction procedure during the anodizing step), attaching a support to the porous anodic film and separating the film along the weakened stratum. If the support is perforated the resulting structure is suitable as a separation device. If imperforate, the support can subsequently be perforated, if required, or replaced by a perforate support or supporting structure. The resulting structure has a non-metallic imperforate or perforated supporting layer (made, for example of plastic or ceramic) or other supporting structure, reinforcing a porous anodic film in which the pores completely penetrate the film.

DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MC	Monaco
AU	Australia	FI	Finland	MG	Madagascar
BB	Barbados	FR	France	ML	Mali
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Fasso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GR	Greece	NL	Netherlands
BJ	Benin	HU	Hungary	NO	Norway
BR	Brazil	IT	Italy	PL	Poland
CA	Canada	JP	Japan	RO	Romania
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
DE	Germany	LU	Luxembourg	TD	Chad
DK	Denmark			TG	Togo
				US	United States of America

POROUS MEMBRANES SUITABLE FOR SEPARATION DEVICES AND OTHER
USES

TECHNICAL FIELD

This invention relates to porous membranes suitable
5 for separation devices, e.g. those used to separate
constituent elements of a mixture of materials of
different particle or molecule size, and for other uses.

BACKGROUND ART

There are many ways of producing perforate solid
10 materials useful for separation devices and the like, but
such procedures generally cannot produce very thin
perforate membranes having very narrow pores which are
desired in many filtering and similar applications in
order, for example, to reduce back pressures, to increase
15 concentration gradients, and to enable smaller particles
to be separated.

It is known that porous oxide films can be grown on
certain metals, most notably aluminum and anodizable
aluminum alloys, by anodizing such metals in electrolytes
20 containing strong acids, such as sulfuric acid and
phosphoric acid and films of this type have been suggested
for use in filter devices (see U.S. patent 3,850,762
issued on November 26, 1974 to A. W. Smith). Anodic films
can be made very thin (e.g. in the order of nanometers)
25 and can be grown to any desired larger thicknesses by
continuing the anodization process for a suitable length
of time. However, it has not generally been convenient to
use such films for separation devices and other similar
purposes for two basic reasons. First of all, anodic
30 films adhere tenaciously to the underlying metal on which
they are formed and cannot easily be removed without
resorting to dissolving away the metal substrate (a slow
and expensive procedure). Secondly, anodic films produced
by porous anodization have imperforate barrier layers at
35 the bases of the pores, immediately adjacent to the metal
substrate, so this layer has to be removed if the film is
to be used in a device which requires complete penetration

of the film, but its removal is very difficult without damaging the remaining porous structure.

We have previously found (see, for example, our European Patent Application Serial No. 0 178 831 published on April 23, 1986, the disclosure of which is incorporated herein by reference) that the adhesion of an anodic film to an underlying metal substrate can be considerably reduced by a pore branching procedure carried out during the porous anodization step, and that the anodic film (which detaches spontaneously or after a period of soaking) thus produced has pores which extend completely from one surface of the film to the other. It is suggested in the published application that the porous anodic films are self-supporting when thick enough (e.g. 50 microns or thicker) but that thin films (0.1 microns to 50 microns) may need to be supported on a porous substrate. It is not easy, however, to attach such free standing films to a suitable support nor to detach such films from the underlying metal in a reliable way when large areas are involved. Films of less than about 25 microns in thickness are particularly difficult to handle in a manufacturing environment. Consequently, porous anodic films have not found widespread use as porous membranes for filters and other devices.

DISCLOSURE OF THE INVENTION

An object of the present invention is to provide a process for producing a very thin porous membrane suitable for separation devices and other purposes.

Another object of the invention is to provide separation devices incorporating very thin porous membranes having very narrow pores.

SUMMARY OF THE INVENTION

According to one aspect of the invention, there is provided a process for producing a porous membrane characterized by porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum

in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous anodic film, and separating at least an outer part of said film from said metal substrate to form a porous membrane supported on said support.

If necessary, the porous membrane attached to the support can be transferred to a different support, e.g. a perforated support, suitable as part of a separation device or other device.

According to another aspect of the invention there is provided a process for producing a separation device, which comprises porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous anodic film, separating at least an outer part of said film attached to said support from said metal substrate at said weakened stratum and, if said support is insufficiently perforated for the laminate of the support and the outer film part to act as a suitable separation device, carrying out a further step selected from the group consisting of perforating said support and replacing said support with a perforated supporting structure.

The invention also relates to supported porous membranes and separation devices.

By the term "perforated" support or supporting structure, we mean to include a continuous layer or body having penetrating holes, a mesh or web made up of fibres or filaments having gaps between the fibres or filaments, or any kind of reinforcements which leave clear access to at least some of the pores of the membrane.

The present invention enables the thin porous membrane to be supported during detachment of the anodic film from the metal substrate on which it is formed and during subsequent handling. This means that the membrane

can be made very thin (less than 50 microns, for example, and even less than 0.5 microns) and that membranes of large area (e.g. greater than 50 square centimetres) can be formed and incorporated into final products.

5 Furthermore, because the membrane is supported and can therefore be made thinner than would otherwise be the case, the anodizing process time can be considerably reduced (e.g. by a factor of 20-30 if supported membranes only a few microns in thickness are adequate and 100 or
10 more if membranes of submicronic thickness are desired). Not only does this save energy and result in thinner membranes which are more flexible and have lower flow resistance, but it also means that closer control of pore size may be more readily accomplished. If processing
15 times are long, considerable dissolution occurs along the length of the pore due to the dwell time in the acidic electrolyte and asymmetric pores may be produced. In the present invention, the pores may be made more symmetrical throughout the thickness of the membrane.

20 The fact that the porous membrane is securely supported also has the advantage that any resulting separation device can be cut by mechanical means or by laser into suitable shapes with reduced risk of splitting or cracking as can be the case with unsupported films.

25 BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a cross-section of a porous anodic film produced by a conventional porous anodization technique;

Fig. 2 is a cross-section of a porous anodic film having a weakened stratum at the oxide/metal interface;

30 Fig. 3 is a cross-section of a film similar to that of Fig. 2 having an attached perforated support; and

Fig. 4 is a cross-section of an apparatus used for the process.

MODES FOR CARRYING OUT THE INVENTION

35 The invention is described in more detail by first explaining a preferred embodiment with reference to the accompanying drawings and then discussing variations and

alternatives to the steps and structures disclosed.

Fig. 1 is a cross-section through a porous anodic film produced in the conventional manner. The film 10 is grown on a substrate 11, which is generally made of aluminum or an anodizable aluminum alloy, by anodizing the substrate at a voltage of 1-1000 volts, more usually 3-200 volts and more preferably 5-80 volts, in an electrolyte containing an acid such as phosphoric acid, sulfuric acid or oxalic acid. The film contains pores 12 which extend inwardly from the outer surface 14 of the film towards the metal substrate 11. However, the pores are separated from the metal by an imperforate barrier layer 10a which adheres tenaciously at the metal/oxide interface.

Fig. 2 shows a similar cross-section of a porous anodic film 10 formed by a similar porous anodization technique. However, in this case, the final stage of the anodization is modified to produce a region of branched pores 15 at the base of each pore 12 by a voltage-reduction procedure as disclosed in our published European patent application referred to above. Basically this involves varying the voltage in a continuous or stepwise manner. For example, the anodization voltage may be reduced from the original anodization voltage about 25 V to 0 V in 0.5 V increments. The voltage reduction has the effect of causing single pores to branch into numerous small pores that weaken the film.

Collectively, the branched pore regions 15 introduce a weakened stratum into the anodic film 10 adjacent to the metal/oxide interface and the film can be separated fairly easily along this stratum. As noted above, it has been found that the barrier layer 10a of Fig. 1 is extremely thin at the end of the pore branching step and is either destroyed or left behind when the film is separated along the weakened stratum, so that the pores 12 in the detached part of the film (the porous membrane) are open at both opposed surfaces of the detached film and completely penetrate the film.

In any event, the pore branching step should be kept reasonably short in terms of time to prevent premature separation of the film.

If desired, further porous anodization can be carried out after the pore branching step. This prolongs the pores beneath the weakened zone without causing the upper film part to spall off and without compromising the release capability. The weakened stratum can thus be removed from the metal/oxide interface which may give a cleaner separation (fewer defects) if there are localized effects caused by the substrate.

Prior to detaching the porous membrane from the metal substrate, a supporting layer 20 (which in this embodiment is itself perforate but need not be) is attached to the outer surface of the film 10 as shown in Fig. 3. The layer 20 preferably has perforations 21 which are quite large compared to the width of the pores 12 in the anodic membrane and can be made, for example, by punching holes in an originally impermeable layer. The layer 20 in this embodiment is a plastic film adhered or heat sealed to the anodic film.

The ratio of the size of the perforations to the thickness of the detached film can be important in some cases when the resulting device is to be used as a separation device. The detached film is essentially unsupported in the areas that lie within the perforations 21. Thinner anodic films require more support than thicker films because of their resulting fragility and so it may be necessary to reduce the width of the perforations 21 as the thickness of the membrane (10) decreases. As a rule of thumb, the diameter of the perforations should be less than the membrane thickness for very thin films. Normally, the perforations range in size from 0.1 micron for very thin membranes (e.g. 0.1 micron) to 500 microns for thicker membranes.

If the layer 20 is flexible, it can be used to assist the detachment of the anodic film from the metal substrate. For example, a part of the layer may extend

2 // 5 beyond the anodic film 10 at an edge in order to form a graspable tab and the tab may be used to peel the layer and attached upper anodic film part (porous membrane) from the underlying structure. When the membrane 10 is quite thin (e.g. less than 30 microns and preferably less than 5 microns), it is quite flexible and the bending of the membrane caused when the layer 20 is peeled from the metal substrate does not usually result in damage to the membrane. However, such bending of the membrane can be avoided entirely, if desired, if the substrate metal 11 is itself made thin and flexible and the layer 20 is made less flexible than the substrate 11. The substrate 11 can then be peeled away from the supporting layer 20 and the adhering membrane 10 without bending the membrane.

15 Having described one embodiment of the invention above, certain variations and alternatives will be discussed in the following.

20 First of all, it should be appreciated that a stratum of weakness can be introduced into the anodic film by means other than the voltage reducing step mentioned above. A similar effect can be obtained by a voltage increase, a change of current wave form (e.g. from a.c. to d.c.), or a change of anodizing acid, individually or in combination.

25 Secondly, there can be considerable variation associated with the support 20. Not only can the nature of the support be varied widely, but the support may also be subsequently removed and replaced by another support or supporting structure. If the membrane is to be used to form a separation device, the final support should itself be perforate. However, if the original support is to be replaced, it need not be perforated because it can be replaced by a perforated member, but even if the support is to remain, it need not be perforated initially since it can be perforated after the detachment of the membrane from the substrate, e.g. by the use of a laser to burn holes in the support or by dissolution or degradation

35

[Handwritten signature]

(e.g. by exposing the film to degrading UV radiation from a flash lamp or the like through the anodic film which acts as a mask except in the area of the pores, or by using the anodic film as a resist for a dissolution process).

Replacement of the support can be carried out by sandwiching the laminate of the porous membrane and the support between a pair of fine mesh grids (made for example of TEFLON or stainless steel) and dissolving or burning away the original substrate *in situ*. The mesh grids can then form the supporting structure for subsequent handling even though they may not be bonded to the anodic film.

After removal of the original support, or even before the original support is applied, selected pores in the membrane may be filled with a material (e.g. a settable liquid such as a lacquer or a polymer solution) that itself reinforces the film. If a suitable pattern of application is selected, such as a dot or grid pattern, good support may be provided while maximizing the areas of unfilled pores. The material penetrating the pores in this way can act alone as a supporting structure after the original support has been removed or it can provide additional support in combination with a porous layer or other support structure.

When the support is a porous layer of the type shown in Fig. 3, it may be organic, such as the polymeric film already mentioned, or inorganic, such as a ceramic. For example, the porous membrane may be incorporated into a porous composite structure of the type disclosed in our co-pending British patent application serial number 8912425.9 filed on May 31, 1989, the disclosure of which is incorporated herein by reference. In such a composite, the porous membrane is integrally bonded to an overlying layer of partly sintered inorganic particles by one of two methods. In the first method, a slurry of inorganic particles is "tape cast" onto the membrane surface and

then heated to partly sinter the particles together. In the second method, a slurry of inorganic particles is tape cast onto the surface, a preformed layer of sintered particles is then applied on top and finally the coatings are heated. In each case the average pore size of the ceramic layer is larger than the average minimum pore size of the porous membrane.

→ When a polymer layer is used as the support, it may be adhered or heat sealed to the anodic film, as briefly mentioned above. Hot melt interfacing materials can be applied in preprogrammed patterns or designs. This provides a meltable layer between the anodic membrane and the support. Alternatively, iron-on interfacing, normally used for stiffening fabrics, can be used to attach a supporting layer, such as a porous nylon mesh, to the anodic film. If the support is to be adhered to the anodic film, this may be done by the spot application of adhesive or polymer solution, e.g. using ink jet printing techniques, to prevent complete blocking of the pores. Yet another attachment technique involves so-called heat staking a porous polymeric membrane of polypropylene, if necessary facilitated by the use of a laser.

The above description has been concerned mainly with the attachment of the porous anodic membrane to a porous support in order to form a separation device. However, the membrane may be attached to an imperforate support in order to form other types of devices, such as catalyst supports and the like. Whether porous or non-porous, the layers used to support the porous membrane are preferably polymeric and are advantageously heat sealed to the membrane.

Returning to the anodizing step of the invention, not only does the use of low anodization voltages produce anodic films having fine pores, which are desirable in most cases, but it also results in low heat evolution and this means that the substrate can be a thin gauge foil, rather than a thick layer or plate, without the risk of

"burning" during anodizing. Because of their thinness and flexibility, foil substrates make it possible to operate the process on a continuous or semi-continuous basis. An example of the process and suitable apparatus therefor is shown in Fig. 4. Aluminum foil 30 is withdrawn from a roll 31 and passed over a roller 32 which acts as a positive electrode. The foil then passes through a bath 33 holding an acidic electrolyte (H_3PO_4). The walls of the bath form the cathode and porous anodization of the film takes place.

Upon emerging from the bath 33, the foil is then passed through a further bath 35 also containing an acidic electrolyte 36 for the introduction of the weakened stratum. The bath has electrically separate vertically disposed side wall sections which act as cathodes 37, 38, 39, 40 each of which exerts a reduced potential.

The resulting anodized foil bearing an anodic film containing a weakened stratum is fed past a roll 41 which applies a porous polymer support. The laminate of the foil, film and support then passes roll 42 which detaches the foil and re-rolls it for further use. The remaining support and film combination 43 is then fed to suitable rolling or cutting equipment (not shown).

If higher voltages are required, making the use of foil difficult, the process can still be made continuous by using a metal substrate in the form of a metal drum slowly rotating in an electrolysis bath with the support being continuously applied and detached as in the case of the foil embodiment.

Various other modifications and variations will occur to persons skilled in the art after reading the disclosure above. All such modifications and variations form part of this invention to the extent that they fall within the scope of the following claims.

CLAIMS:

1. A process for producing a porous membrane characterized by porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said
5 film having an outer surface, creating a weakened stratum in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous anodic film, and separating at least an outer part of said film from said
10 metal substrate to form a porous membrane supported on said support.
2. A process according to claim 1 characterized in that said weakened stratum is created in said film by reducing an anodizing voltage used for said anodizing step as a
15 final part of said anodizing step.
3. A process according to claim 1 characterized in that said weakened stratum is created in said film by increasing an anodizing voltage used for said anodizing step as a final part of said anodizing step.
- 20 4. A process according to claim 1 characterized in that said anodizing step is carried out with a current having a particular waveform and said weakened stratum is created by changing said waveform.
5. A process according to claim 1 characterized in that
25 said anodizing step is carried out in an electrolyte containing a particular acid and said weakened stratum is created by replacing said acid after a first period of anodizing with a different acid and continuing said anodizing step.
- 30 6. A process according to claim 1, claim 2, claim 3, claim 4, or claim 5 characterized in that said support is perforated.
7. A process according to claim 6 characterized in that said support is a layer of organic material.
- 35 8. A process according to claim 7 characterized in that said organic material is a polymer attached to said anodic film by means of an adhesive applied to limited areas of

said film to minimize blocking of pores in said film.

9. A process according to claim 6 characterized in that said support is a layer of ceramic attached by sintering said ceramic to said anodic film.

5 10. A process according to claim 1, claim 2, claim 3, claim 4, or claim 5 characterized in that said support is imperforate and said support is perforated after said separation of said film from said substrate.

10 11. A process according to claim 10 characterized in that said support is perforated by a procedure selected from the group consisting of dissolution and degradation.

12. A process according to claim 10 characterized in that said support is perforated by means of a laser.

15 13. A process according to claim 1, claim 2, claim 3, claim 4 or claim 5 characterized in that said support is replaced by a porous supporting structure by positioning said support and porous membrane between porous webs of material and removing said support by a method selected from the group consisting of dissolving and burning.

20 14. A process according to claim 1, claim 2, claim 3, claim 4 or claim 5 characterized in that a reinforcing material is introduced into pores in limited areas of said porous anodic film in order to form an integral porous supporting structure. 15. A process according to claim 1, 25 claim 2, claim 3, claim 4 or claim 5 characterized in that said substrate is less flexible than said support and wherein said separation of said film is carried out by peeling said support away from said substrate.

30 16. A process according to claim 1, claim 2, claim 3, claim 4 or claim 5 characterized in that said substrate is more flexible than said support and wherein said separation of said film is carried out by peeling said substrate away from said support.

35 17. A process according to claim 1, claim 2, claim 3, claim 4 or claim 5 characterized in that said substrate is a flexible metal foil and wherein said process is carried out continuously by passing an elongated web of said foil

through an electrolysis bath, continuously attaching said support to the resulting porous anodic film as the web emerges from the bath and continuously detaching said support and at least said outer film part from said substrate.

18. A process for producing a separation device, which comprises porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous anodic film, separating at least an outer part of said film attached to said support from said metal substrate at said weakened stratum and, if said support is insufficiently perforated for the laminate of the support and the outer film part to act as a suitable separation device, carrying out a further step selected from the group consisting of perforating said support and replacing said support with a perforated supporting structure.

19. A porous membrane characterized in that it is produced by porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous anodic film, and separating at least an outer part of said film from said metal substrate to form a porous membrane supported on said support.

20. A separation device characterized in that it is produced by a process which comprises porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum in said porous anodic film without causing said film to separate at said weakened stratum, attaching a support to said outer surface of said porous

anodic film, separating at least an outer part of said film attached to said support from said metal substrate at said weakened stratum and, if said support is

insufficiently perforated for the laminate of the support
5 and the outer film part to act as a suitable separation device, carrying out a further step selected from the group consisting of perforating said support and replacing said support with a perforated supporting structure.

21. A supported porous membrane comprising a porous
10 membrane attached to a layer of non-metallic material as a support, characterized in that the porous membrane is a porous anodic film.

22. A supported porous membrane according to claim 21
15 characterized in that all said non-metallic material is a polymeric material.

23. A separation device comprising a porous film attached to a porous layer of non-metallic material used as a support, characterized in that the porous film is a porous anodic film.

20 24. A separation device according to claim 23 characterized in that said non-metallic material is a polymeric material.

25 25. A membrane according to claim 19, claim 21 or claim 22 characterized in that said film has a thickness of less than 50 microns.

26. A membrane according to claim 19, claim 21 or claim 22 characterized in that said film has a thickness of less than 15 microns.

30 27. A membrane according to claim 19, claim 21 or claim 22 characterized in that said outer part of said film has an area of at least 50 square centimetres.

28. A membrane according to claim 19, claim 21 or claim 22 characterized in that said film is supported by a supporting structure comprising a reinforcing material in
35 pores in selected areas of said porous anodic film.

29. A separation device according to claim 20, claim 23 or claim 24 characterized in that said film has a

thickness of less than 50 microns.

30. A separation device according to claim 20, claim 23 or claim 24 characterized in that said film has a thickness of less than 15 microns.

5 31. A separation device according to claim 20, claim 23 or claim 24 characterized in that said outer part of said film has an area of at least 50 square centimetres.

32. A separation device according to claim 20, claim 23 or claim 24 characterized in that said film is supported
10 by a supporting structure comprising a reinforcing material in pores in selected areas of said porous anodic film.

[received by the International Bureau on 19 February 1991 (19.02.91); original claims 24, 28-32 cancelled; claim 1 amended; new claims 2 and 20 added; original claims 2-18 renumbered as claims 3-19 wherein original claims 2-5, 10, 15-18 are amended; claims 19-22 and 23 replaced by amended claims 21-24 and 28; original claims 25-27 amended (4 pages)]

1. A process for producing a supported porous membrane by porous anodizing a suitable metal substrate to form a porous anodic film on said metal, said film having an outer surface, creating a weakened stratum in said porous anodic film, detaching said porous anodic film from said substrate and supporting said porous film on a support to form a porous membrane supported on said support, characterized in that said support is attached to said outer surface of said anodic film prior to detachment of said anodic film from said substrate.
2. A process according to claim 1 characterized in that said weakened stratum is formed in said porous anodic film at a distance from said substrate so that an inner part of said film remains attached to said substrate after detachment of an outer part of said film.
3. A process according to claim 1 characterized in that said weakened stratum is created in said film by reducing an anodizing voltage used for said anodizing step.
4. A process according to claim 1 characterized in that said weakened stratum is created in said film by increasing an anodizing voltage used for said anodizing step.
5. A process according to claim 1 characterized in that said anodizing step is carried out with a current having a particular waveform and said weakened stratum is created by changing said waveform.
6. A process according to claim 1 characterized in that said anodizing step is carried out in an electrolyte containing a particular acid and said weakened stratum is created by replacing said acid with a different acid.
7. A process according to claim 1, claim 2, claim 3, claim 4, claim 5 or claim 6 characterized in that said support is perforated.
8. A process according to claim 7 characterized in that said support is a layer of organic material.
9. A process according to claim 8 characterized in that said organic material is a polymer attached to said anodic film by means of an adhesive applied to limited areas of

said film to minimize blocking of pores in said film.

10. A process according to claim 7 characterized in that said support is a layer of ceramic attached by sintering said ceramic to said anodic film.

5 11. A process according to claim 1, claim 2, claim 3, claim 4, claim 5 or claim 6 characterized in that said support is imperforate and said support is perforated after said detachment of said film from said substrate.

12. A process according to claim 11 characterized in that
10 said support is perforated by dissolution or degradation.

13. A process according to claim 11 characterized in that said support is perforated by means of a laser.

14. A process according to claim 1, claim 2, claim 3, claim 4, claim 5 or claim 6, characterized in that said
15 support is replaced by a porous supporting structure by positioning said support and porous membrane between porous webs of material and removing said support by dissolving or burning.

15. A process according to claim 1, claim 2, claim 3,
20 claim 4, claim 5 or claim 6, characterized in that a reinforcing material is introduced into pores in limited areas of said outer part of said porous anodic film in order to form an integral porous supporting structure.

16. A process according to claim 1, claim 2, claim 3,
25 claim 4, claim 5 or claim 6, characterized in that said substrate is less flexible than said support and in that said detachment of said film is carried out by peeling said support away from said substrate.

17. A process according to claim 1, claim 2, claim 3,
30 claim 4, claim 5 or claim 6, characterized in that said substrate is more flexible than said support and in that said detachment of said film is carried out by peeling said substrate away from said support.

18. A process according to claim 1, claim 2, claim 3,
35 claim 4, claim 5 or claim 6, characterized in that said substrate is a flexible metal foil and in that said process is carried out continuously by passing an elongated web of said foil through an electrolysis bath,

porous anodic film as the web emerges from the bath and continuously detaching said support and said outer film part from said substrate.

19. A process for producing a separation device by porous
5 anodizing a suitable metal substrate to form a porous
anodic film on said substrate, said film having an outer
surface, creating a weakened stratum in said porous anodic
film, detaching said porous anodic film from said
substrate and supporting said porous film on a porous
10 support suitable to form a separation device,
characterized in that said support is attached to said
outer surface of said anodic film prior to detachment of
said anodic film from said substrate, and in that, if said
support is insufficiently perforate to form a separation
15 device, a further step of perforating said support or
replacing said support with a suitably perforate
supporting structure is carried out.

20. A process according to claim 19 characterized in that
said weakened stratum is formed in said porous anodic film
20 at a distance from said substrate so that an inner part of
said film remains attached to said substrate after
detachment of an outer part of said film.

21. A supported porous membrane characterized in that it
is produced by a process according to claim 1, claim 2,
25 claim 3, claim 4, claim 5, claim 7, claim 8, claim 9,
claim 11, claim 12 or claim 13.

22. A separation device characterized in that it is
produced by a process according to claim 19 or claim 20.

23. A supported porous membrane comprising a porous
30 anodic film reinforced by a non-metallic material,
characterized in that the non-metallic material is present
in pores in selected areas of said porous anodic film.

24. A supported porous membrane according to claim 23
characterized in that said non-metallic material is a
35 polymeric material.

25. A supported porous membrane according to claim 21,
characterized in that said film has a thickness of less
than 50 microns.

26. A supported porous membrane according to claim 21, characterized in that said film has a thickness of less than 15 microns.

27. A supported porous membrane according to claim 21, 5 characterized in that said film has an area of at least 50 square centimetres.

28. A separation device comprising a porous anodic film supported by a material suitable to form a separation device and reinforced by a non-metallic material, 10 characterized in that said non-metallic material is present in pores in selected areas of said porous anodic film.

STATEMENT UNDER ARTICLE 19 (1)

The amended claims are of more limited scope than the original claims.

In particular, the process claims have been limited to the step of attaching the support to the anodic film prior to detachment of the film from the substrate.

New claims 2 and 20 relate to the formation of the weakened stratum within the anodic film at positions spaced from the substrate.

This feature is disclosed on page 6, lines 8 to 11 and its purpose is to produce a cleaner separation of the anodic film from the substrate.

Independent claims 23 and 28 for a supported porous membrane and separation device are limited to the feature of former claim 28, i.e. reinforcement within the pores.




FIG. 1




FIG. 2




FIG. 3





FIG. 4

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) * According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁵ : B 01 D 71/02, // C 25 D 11/02						
II. FIELDS SEARCHED <div style="text-align: right; font-size: small;">Minimum Documentation Searched ?</div> <table style="width: 100%; border: none;"> <tr> <td style="width: 30%; border: none;">Classification System</td> <td style="border: none;">Classification Symbols</td> </tr> <tr> <td style="border: none; padding-top: 10px;">IPC⁵</td> <td style="border: none; padding-top: 10px;">B 01 D 71/00, C 25 D 11/00</td> </tr> </table> <div style="text-align: center; font-size: x-small; margin-top: 10px;"> Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched * </div>			Classification System	Classification Symbols	IPC ⁵	B 01 D 71/00, C 25 D 11/00
Classification System	Classification Symbols					
IPC ⁵	B 01 D 71/00, C 25 D 11/00					
III. DOCUMENTS CONSIDERED TO BE RELEVANT *						
Category *	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³				
A	EP, A, 0242204 (ALCAN INTERNATIONAL LTD) 21 October 1987 <div style="text-align: center;">---</div>					
A	EP, A, 0178831 (ALCAN INTERNATIONAL LTD) 23 April 1986 cited in the application <div style="text-align: center;">---</div>					
A	Chemical Abstracts, volume 80, no. 26, 1 July 1974, (Columbus, Ohio, US), see page 428, abstract no. 152076u & JP, A, 7244418 (SUMITOMO ELECTRIC INDUSTRIES, LTD) 9 November 1972 <div style="text-align: center;">-----</div>					
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>* Special categories of cited documents: ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>						
IV. CERTIFICATION						
Date of the Actual Completion of the International Search <div style="text-align: center; font-size: large;">27th November 1990</div>	Date of Mailing of this International Search Report <div style="text-align: center; font-size: large;">18 DEC 1990</div>					
International Searching Authority <div style="text-align: center; font-weight: bold;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center;">  MISS P. TAZELAAR </div>					

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.

CA 9000329

SA 40314

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 11/12/90. The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A- 0242204	21-10-87	AU-B- 592863	25-01-90
		AU-A- 7155387	22-10-87
		JP-A- 62270794	25-11-87
		US-A- 4889631	26-12-89
EP-A- 0178831	23-04-86	AU-B- 569576	04-02-88
		AU-A- 4878085	24-04-86
		CA-A- 1266251	27-02-90
		JP-A- 61106796	24-05-86
		US-A- 4687551	18-08-87